

> **Gas & Metal Compatibility Table**

Gas	Chemical Formula	Suggested Filter Media
Ammonia	NH <sub>3</sub>	SS/Ni
Argon	Ar	SS/Ni
Arsenic Pentafluoride	AsF <sub>5</sub>	SS/Ni
Arsine	AsH <sub>3</sub>	SS/Ni(1)
Boron Trichloride	BCl <sub>3</sub>	Ni/H
Boron Trifluoride	BF <sub>3</sub>	Ni/H
Carbon Dioxide	CO <sub>2</sub>	SS/Ni
Carbon Monoxide	CO	SS
Carbon Tetrachloride	CCl <sub>4</sub>	SS/Ni
Carbon Tetrafluoride	CF <sub>4</sub>	SS/Ni
Chlorine	Cl <sub>2</sub>	SS/Ni/H
Diborane	B <sub>2</sub> H <sub>6</sub>	SS/Ni(1)
Dichlorosilane	SiH <sub>2</sub> Cl <sub>2</sub>	Ni/H
Diethyltelluride	C <sub>4</sub> H <sub>10</sub> Te	SS/Ni
Fluorine	F <sub>2</sub>	Ni/H
Freon 13	CClF <sub>3</sub>	SS/Ni
Freon 14 Tetrafluoromethane	CF <sub>4</sub>	SS/Ni
Freon 23 Trifluoromethane/Fluoro-form	CHF <sub>3</sub>	SS/Ni
Freon 115 Chloropentafluoroethane	C <sub>2</sub> ClF <sub>5</sub>	SS/Ni
Freon 116 Hexafluoroethane	C <sub>2</sub> F <sub>6</sub>	SS/Ni
Germane	GeH <sub>4</sub>	SS/Ni
Helium	He	SS/Ni
Hydrogen	H <sub>2</sub>	SS/Ni
Hydrogen Bromide	HBr	Ni/H
Hydrogen Chloride	HCl	Ni/H
Hydrogen Fluoride	HF	Ni/H
Hydrogen Selenide	H <sub>2</sub> Se	SS/Ni
Hydrogen Sulfide	H <sub>2</sub> S	SS/Ni
Krypton	Kr	SS/Ni
Methane	CH <sub>4</sub>	SS/Ni
Methyl Fluoride	CH <sub>3</sub> F	SS/Ni
Nitric Oxide	NO	SS/Ni
Nitrogen	N <sub>2</sub>	SS/Ni
Nitrogen Trifluoride	NF <sub>3</sub>	SS/Ni/H
Nitrous Oxide	N <sub>2</sub> O	SS/Ni
Neon	Ne	SS/Ni
Oxygen	O <sub>2</sub>	SS/Ni
Ozone	O <sub>3</sub>	H
Perfluoropropane	C <sub>3</sub> F <sub>8</sub>	SS/Ni
Phosphine	PH <sub>3</sub>	SS/Ni(1)
Phosphorus Trifluoride	PF <sub>3</sub>	Ni/H
Phosphorous Pentachloride	PCl <sub>5</sub>	SS/Ni
Phosphorous Pentafluoride	PF <sub>5</sub>	SS/Ni
Silane	SiH <sub>4</sub>	SS/Ni
Silicon Tetrachloride	SiCl <sub>4</sub>	Ni/H
Silicon Tetrafluoride	SiF <sub>4</sub>	Ni/H
Stibine	SbH <sub>3</sub>	SS/Ni
Sulfur Hexafluoride	SF <sub>6</sub>	SS/Ni
Tetraethyl Orthosilicate	TEOS	SS/Ni
Trichlorosilane	SiHCl <sub>3</sub>	Ni/H
Trimethyl Borane	C <sub>3</sub> H <sub>9</sub> B	SS/Ni
Trimethyl Phosphate	C <sub>3</sub> H <sub>9</sub> PO <sub>4</sub>	SS/Ni
Tungsten Hexafluoride	WF <sub>6</sub>	Ni/H
Xenon	Xe	SS/Ni

SS = 316L Stainless Steel  
 Ni = Nickel  
 H = Hastelloy® C-22  
 (1) -Nickel is not compatible with temperatures above 25°C and concentrations below 1,000 ppm

**Choosing a Mott High Purity Gas Filter:**

Choosing the best metal filter is not always a simple matter, because in addition to easily identified variables (i.e., gas, pressure and flow), there are subjective considerations. Some gases are compatible with more than one type of metal which allows you a choice when selecting the right filter for your application.

The information contained in this table is a guideline for appropriate filter selection. Consultation with your gas supplier is recommended to ensure gas compatibility. Because so many factors can affect the chemical resistance of a given product, you should pretest under your own operating conditions. As with any chemical application, safety precautions as noted on MSDS sheets should be observed.



Mott engineers are available to recommend which filter best meets the criteria of your application. To expedite that selection process, you should have the following information available:

Type of Gas: \_\_\_\_\_

Gas Flow Rate: \_\_\_\_\_

Inlet (or system) Pressure: \_\_\_\_\_ PSIG

Maximum allowable ΔP: \_\_\_\_\_ PSID

Inlet & Outlet Connections: \_\_\_\_\_

Available Envelope/Footprint Dimensions (if known): \_\_\_\_\_

Mott Corporation has High Purity Distributors worldwide. Visit our website [www.mottcorp.com](http://www.mottcorp.com) and click on the Contact Us button to locate one in your area.

> **high purity products**